

Nail polish

with CITROFOL®



Phase	Ingredients	INCI	Supplier	Quantity
A	Pigment		Sensient	3.00 %
	Butyl Acetate	Butyl Acetate		15.00 %
	Ethyl Acetate	Ethyl Acetate		15.00 %
B	Nitrocellulose E32	Nitrocellulose	Synthesia	4.00 %
	Nitrocellulose E27	Nitrocellulose	Synthesia	9.50 %
	Nitrocellulose E23	Nitrocellulose	Synthesia	5.00 %
	CITROFOL® BII	Acetyl Tributyl Citrate	Jungbunzlauer	5.50 %
	Butyl Acetate	Butyl Acetate		17.00 %
	Ethyl Acetate	Ethyl Acetate		10.00 %
	Isopropyl Alcohol	Isopropyl Alcohol		6.00 %
	BELSIL P 1101	Alcohol, Crotonic Acid/Vinyl C8-12 Isoalkyl Esters/VA/Bis-Vinylidimethicone Crosspolymer	Wacker Chemie AG	10.00 %

Jungbunzlauer

*From nature
to ingredients®*

Directions

- 1 Premix phase A and phase B separately and stir until homogeneity
- 2 Add phase A into phase B while stirring

Technical Data

Appearance: coloured liquid

Stability

Stable for 3 months at RT, 5 °C (41 °F), 40 °C (104 °F)



Headquarters **Jungbunzlauer Suisse AG** · CH-4002 Basel · Switzerland · Phone +41-61-2955 100
For further information please contact: headquarters@jungbunzlauer.com
www.jungbunzlauer.com

The information contained herein is meant to demonstrate how our products can be used. This formulation has been subjected to limited stability tests and has been shown to perform well. The given data are suggestions without any guarantee aimed to support customers' development.